



Experience Excellence  
In Glass Beads



## Technical Data Sheet

ROAD MARKING | Drop-On | **Echostar®** |

**Main use** | High quality drop-on beads according to EN1423, CE mark |

**Chemical composition** | Soda lime glass |

**Particle size distribution** |

µm	1700	1400	1180	1000	850	710	600	500	425	355	300	250	212	180	150	125	Nominal sieves (µm)						
				0-2	0-2	0-10	5-40			40-80			70-100			95-100	710-125	↓	<b>Echostar® 5</b>				
					0-10			20-60			45-85			75-100		95-100	850-125	↓	<b>Echostar® 10</b>				
			0-2										70-100			95-100	1180-125	↓	<b>Echostar® 20</b>				
				0-2									95-100				1180-212	↓	<b>Echostar® 25</b>				
																	1400-212	↓	<b>Echostar® 30</b>				
<b>Main uses and coatings</b>																							
Thermoplastic						TRM		TRM															
Solvent based paints						SBP ECO		SBP ECO															
Solvent non aromatic paints						SBP ECO		SBP ECO															
Water-borne paints						WBP		WBP															
2 components						BCP		BCP															

- **Roundness - quality** | > 80% |
- **Refractive index** | Class A > 1.5 |
- **Physical and chemical resistance** | in accordance with EN1423 |
- **Dangerous substances** | Class 1 |
- **Labelling - Markings** | CE mark according to EN1423 | Benor for Begium | Others standards, contact us |
- **Packaging** | Black bags of 25 kg net |
- **Shelf Life** | 12 months from manufacturing date |
- **User advices** | Contact us for any questions |