



Experience Excellence
In Glass Beads



Technical Data Sheet

ROAD MARKING | Drop-On | Echostar® BCP Tecno |

Main use | High quality drop-on beads coated with a specific treatment including peroxyde glass beads according to EN1423, CE mark |

Chemical composition | Glass beads based on soda lime composition |

Particle size distribution |

µm	1700			0-2
	1400			0-10
	1180			5-30
	1000		0-2	
	850			40-80
	710	0-10		
	600	5-40		70-100
	500			
	425			80-100
	355	40-80		90-100
	300			
	250			
	212	70-100		95-100
	180			
	150			
	125	95-100		
Nominal sieves (µm)		710-125		1400-212
Main uses and coatings		Echostar® 5 BCP Tecno		Echostar® 30 BCP Tecno
		Type 1		Type 2
2 components liquid solid		BCP Tecno		BCP Tecno

- Roundness - quality | > 80% |
- Refractive index | Class A > 1.5 |
- Physical and chemical resistance | In accordance with EN1423 |
- Dangerous substances | Class 1 |
- Labelling - Markings | CE mark according to EN1423 | Benor for Belgium | Others standards, contact us |
- Packaging | Many, contact us |
- Shelf Life | 12 months from manufacturing date below 35°C |
- User advices | Contact us for any questions |